



Sinclair, M. et al. (2019) High-Q Si<sub>3</sub>N<sub>4</sub> Ring Resonators for Locking 780nm GaAs-Based Distributed Feedback Laser. In: 2019 Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC), Munich, Germany, 23-27 Jun 2019, ISBN 9781728104690 (doi:[10.1109/CLEOE-EQEC.2019.8872725](https://doi.org/10.1109/CLEOE-EQEC.2019.8872725)).

This is the author's final accepted version.

There may be differences between this version and the published version. You are advised to consult the publisher's version if you wish to cite from it.

<http://eprints.gla.ac.uk/205454/>

Deposited on: 11 December 2019

Enlighten – Research publications by members of the University of Glasgow  
<http://eprints.gla.ac.uk>

# High-Q Si<sub>3</sub>N<sub>4</sub> ring resonators for locking 780nm GaAs-based distributed feedback laser

M. Sinclair<sup>1</sup>, K. Gallacher<sup>2</sup>, R. W. Millar<sup>2</sup>, J. C. Bayley<sup>1</sup>, O. Sharp<sup>3</sup>, F. Mirando<sup>3</sup>, G. Ternent<sup>3</sup>, G. Mills<sup>3</sup>, B. Casey<sup>3</sup>, S. Hild<sup>1</sup>, D.J. Paul<sup>2</sup>

1. School of Physics & Astronomy, University of Glasgow, Kelvin Building, University Avenue, Glasgow, G12 8QQ, U.K.


2. School of Engineering, University of Glasgow, Rankine Building, Oakfield Avenue, Glasgow, G12 8LT, U.K.

3. Kelvin Nanotechnology, Rankine Building, Oakfield Avenue, Glasgow, G12 8LT, U.K.

High-Q microring resonators have applications in gyroscopes, frequency comb generation, and feedback systems to control narrow linewidth integrated lasers [1-3]. This paper demonstrates the highest Q values measured for microring resonators at 780 nm wavelength. These sub mm integrated cavities can be used to provide an error signal for locking a distributed feedback laser (DFB), **Fig. 1(a)**, using the Pound-Drever-Hall (PDH) method. High stability DFBs can also be achieved using a micro-electro-mechanical system (MEMS) cell containing <sup>87</sup>Rb vapour and taking advantage of the absorption line at 780.24 nm. This provides an absolute reference for locking the laser but only to the <sup>87</sup>Rb transition wavelengths. The microring resonator can be tailor made for any wavelength but is susceptible to thermal effects; this could in part be overcome using a top cladding with a thermo-optic coefficient that counteracts that of the waveguide core.

Silicon nitride (Si<sub>3</sub>N<sub>4</sub>) waveguide cores are fabricated from a low-pressure chemical vapour deposition at 750°C. The Si<sub>3</sub>N<sub>4</sub> core material is deposited onto a 4 μm thick thermal SiO<sub>2</sub> layer grown by wet oxidation at 1000°C. The waveguide pattern is written using electron beam lithography and etched using a CHF<sub>3</sub>/O<sub>2</sub> reactive ion etching. A SiO<sub>2</sub> top cladding layer can be added using plasma enhanced chemical vapour deposition at 300°C.

Initial experiments varied the gap spacing between the bus waveguide and microring resonator to find the highest resolvable Q for a given waveguide geometry, **Fig. 1(b)**. As the gap spacing is increased, the power coupling is over-coupled, critically coupled, then under-coupled. The highest measurable Q values are found for under-coupled microrings, this limits application for frequency comb generation but provides the greatest error signal for laser locking. The microrings were measured with and without a top SiO<sub>2</sub> cladding layer. Higher Q values were achieved with the top cladding; when directly comparing microrings with similar power coupling the Q value is shown to approximately double with the addition of the cladding. The most significant loss mechanism at 780nm wavelength is scattering due to line-edge roughness of the etched waveguides. The top cladding layer deposition should have minimal effect on the material absorption suggesting that the loss is limited by scattering. Q can therefore be improved by increasing the waveguide width, **Fig. 1(c)**. This reduces the intensity of the modal field at the waveguide sidewall. With this approach, a Q value of ~800,000 has been demonstrated for microring resonators without a top cladding. For rings with a top cladding, Q values greater than 1 million are expected.



**Fig. 1(a)** A DFB laser coupled to a Si<sub>3</sub>N<sub>4</sub> waveguide on-chip **(b)** Average Q values for 500 nm wide, 200 nm thick, 300 μm radius waveguide microring resonators of varied gap spacing **(c)** Average Q values of 300 μm radius, 200 nm thick waveguide microring resonators of varied waveguide width. Insert: a microscope image of a Si<sub>3</sub>N<sub>4</sub> microring resonator.

## Example References

- [1] M. Á. Guillén-Torres, E. Cretu, N. A. Jaeger, and L. Chrostowski, "Ring resonator optical gyroscopes Parameter optimization and robustness analysis". *Journal of Lightwave Technology*, **30**(12), 1802 (2012)
- [2] P. Del'Haye, A. Schliesser, O. Arcizet, T. Wilken, R. Holzwarth, and T.J. Kippenberg, "Optical frequency comb generation from a monolithic microresonator". *Nature*, **450**(7173), 1214 (2007)
- [3] Y. Ding, G. Ternent, A. Saeed, C. J. Hamilton, N. Hempler, G. P. A. Malcolm, G. T. Maker, M. Sorel, and D. J. Paul. "GaAs-based distributed feedback laser at 780 nm for <sup>87</sup>Rb cold atom quantum technology". *Lasers and Electro-Optics Europe & European Quantum Electronics Conference*, 1 (2017).